

**INSTRUCCIONES DE TRABAJO**

Versión nº: 2 Fecha de revisión: Septiembre 2011

**IDT-605: Fichas técnicas de producto****TECHNICAL DATA****LOOP 001****Características de construcción**

Construcción  
Composición básica  
Acabado

Ancho : < 50 mm  
          ≥ 50 mm  
          ≥ 100 mm

Espesor

Peso

**Características de empleo**

Resistencias mecánicas con cierre HOOK

Pelaje \*

Cizallamiento \*

Vida del cierre \*

Carga de rotura \*

Encogimiento al lavado (3 x 60°C) \*

Solidez color al lavado UNE-EN ISO 105 C-10  
Solidez color al lavado en seco ISO 105 sec/DO1  
Solidez color al frotamiento ISO 105 sec/X12  
Solidez color al agua ISO 105 sec/EO1  
Solidez color al agua de mar ISO 105 sec/EO2  
Solidez color a la luz ISO 105 sec /BO2

Solidez color al sudor ISO 105 sec/EO4

\* Norma interna VESA

Tejido  
Poliamida  
Resina Sintética

Nominal ± 1 mm  
Nominal ± 1.5 mm  
Nominal ± 2 mm

2.35 ± 0.25 mm

300 g/m<sup>2</sup> ± 10 %

Promedio 2.0 N/cm  
Mínimo 1.3 N/cm

Promedio 10.3 N/cm<sup>2</sup>  
Mínimo 7.3 N/cm<sup>2</sup>

Pérdida del 50 % después de 10000 aberturas

Mínimo 210 N/cm

Máximo 4 %

4 mínimo  
4 mínimo  
4 mínimo  
4 mínimo  
4 mínimo  
5 mínimo (colores oscuros)  
4 mínimo (blanco y colores claros)  
3 mínimo (colores fluor)  
4 mínimo

Las indicaciones contenidas en esta hoja de información están basadas en pruebas y ensayos fidedignos. Valor promedio como referencia únicamente, no especificación nominal. Dada la diversidad de usos de nuestros productos, aconsejamos a nuestros clientes se aseguren que el producto cumple con la utilización deseada, asumiendo en este caso responsabilidad de su uso.

**Elaborado:** J.C. Lima

**Revisado:** E. Ducet

**Autorizado:** J. Jacobs

**Fecha:** 27.09.11

**ANEXO: IDT – 605-A**

**FTP 200 Versión 4**

**INSTRUCCIONES DE TRABAJO**

Versión nº: 2 Fecha de revisión: Septiembre 2011

**IDT-605:** Fichas técnicas de producto**TECHNICAL DATA****LOOP 001****Construction characteristics**

Basic construction  
 Base material  
 Standard binder backing

Width : < 50 mm  
 ≥ 50 mm  
 ≥ 100 mm

Overall thickness

Weight

**Usage characteristics**

Peel Strength with Hook std \*

Shear Strength with Hook std \*

Cycle life \*

Breaking Strength \*

Shrinkage after washing ( 3 x 60°C ) \*

Colourfastness to washing UNE-EN ISO 105-C10

Colourfastness to dry cleaning ISO 105 sec/DO1

Colourfastness to rubbing ISO 105 sec/X12

Colourfastness to water ISO 105 sec/EO1

Colourfastness to sea water ISO 105 sec/EO2

Colourfastness to light ISO 105 sec/BO2

Colourfastness to perspiration ISO 105 sec/EO4

\* Internal norm of VESA

Woven  
 Polyamide  
 Synthetic resin  
  
 Nominal ± 1 mm  
 Nominal ± 1.5 mm  
 Nominal ± 2 mm

2.35 ± 0.25 mm

300 g/m<sup>2</sup> ± 10 %

Average 2.0 N/cm  
 Minimum 1.3 N/cm

Average 10.3 N/cm<sup>2</sup>  
 Minimum 7.3 N/cm<sup>2</sup>

50 % loss after 10000 cycles

Minimum 210 N/cm

Maximum 4 %

4 minimum  
 4 minimum  
 4 minimum  
 4 minimum  
 4 minimum  
 5 minimum (dark colours)  
 4 minimum (white and light colours)  
 3 minimum (fluor colours)  
 4 minimum

The information included in this Technical Sheet is based on reliable tests and trials. Average value as a reference only, not a nominal specification. Given the diversity of uses of our products we advise our customers to assure themselves that the product meets the requirements of their application. The responsibility for the application and use of the product remains with the customer.

**Elaborado:** J.C. Lima

**Revisado:** E. Ducet

**Autorizado:** J. Jacobs

**Fecha:** 27.09.11

**ANEXO: IDT – 605-B**

**FTP 200 Versión 4**